

## SILAK SILICONIZED SEALANT Siliconized Acrylic Sealant



### Product Description

Silak Siliconized Sealant is an acrylic polymer-based, silicone emulsion enhanced gap-filling material that adheres on the surface strongly and keeps its flexibility.

### Benefits

- A ready-to-use, one component, joint sealing material
- Over-paintable
- Permanently elastic
- Resistant to abrasion and impacts which do not damage the outer skin
- Maintains its standards between -20°C and +70°C for years

### Applications

Before the application, the tip of the cartridge is cut, and a plastic cap is fixed. The tip of the cap is cut according to the width of the surface and fixed to the cartridge gun. The joints should be filled at one time and without gaps during the application. After the joints are filled with acrylic, the surface is smoothed with a spatula immediately. The adhesive tape should be removed afterwards. The opened packages should be consumed as quickly as possible. In the application environment, decrease in the temperature (max +80°C) and decrease in air humidity accelerate the reaction. The drying period extends at the temperatures below +15°C. Do not apply outdoor in rainy water.

### Health and Safety Information

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Safety Data Sheet.

### Technical Data

<b>Color</b>	Grey
<b>Density (gr/cm<sup>3</sup>)</b>	1,65 ± 0,05
<b>Volume loss at drying (DIN 52451)</b>	~18
<b>Skin Formation Time (min)</b>	~40
<b>Heat Resistance</b>	Between -20°C and +70°C
<b>Working Temperature</b>	Between +5°C and +40°C
Technical data are approximately provided according to temperature of +23°C and a relative humidity of 50%.	

### Cleaning After the Application

- The contaminated areas and used tools should be cleaned with water before the material is dried.
- It is cleaned only mechanically after cured.

### Packaging

500 gr cartridges / 24 pcs in box

### Storage

- They should be protected from water, frost and adverse air conditions.
- They should be kept dry and cool on wooden pallets at
  - Between +10°C and +25°C in moisture free conditions.
- The opened products should be consumed immediately.
- Maximum 8 boxes are stacked on each other.
- Shelf life is maximum 2 years conditional to complying with the abovementioned storage conditions.